

SHAOXING YIWAY IMPORT AND EXPORT CO.,LTD.
ROOM NO.1904, 19TH FLOOR OF DINGSHENG MANSION,NO.375 OF EAST SHEN GLI
ROAD,SHAOXING,ZHEJIANG,CHINA

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : (A)Woven fabric (Woven blackout P/D B1)

Sample Color : (A)BLACK
End Use : (A)curtain fabric
Style No. : A02335
Manufacturer : JINSI GROUP HOLDING CO.,LTD
Origin : China
Other Info. : Exported to: NETHERLANDS

Proposed Care Instruction : -

Sample Receiving Date : Jun 13, 2025
Testing Period : Jun 13, 2025 - Jun 27, 2025
Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the sample(s) tested, for further details, please refer to the following page(s).

Test Performed : Selected test(s) as requested by applicant

Signed for and on behalf of
SGS-CSTC Standards Technical Services (Changzhou) Co., Ltd



Susan Dong (Account Executive)



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/terms-and-conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions. If any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755)8307 1443, or email: CN_Docscheck@sgs.com

Test Result

Textiles and Textile Products - Burning Behaviour - Curtains and Drapes -Classification Scheme#
(EN 13773:2003)

Sample: A

Class specification: Class 1

Detailed Procedure to Determine the Ignitability of Vertically Oriented Specimens(Small Flame)
(EN 1101:1995+A1:2005 (Modified); EN ISO 6940:1995)

After 100 washes

Ignition time (s)	Lengthwise	Widthwise
1	N	N
2	N	N
3	N	N
4	N	N
5	N	N
10	N	N
15	N	N
20	N	N

Remark:

- "Y" : Ignition ; "N" : Non-ignition
- Ignition shall be deemed to have occurred if flaming of the specimen which gives an Afterflame time of 5s or more or which reaches the top or vertical edges in less than 5s.
- Burner ignition location: Bottom edge ignition
- Ignition time: 1-5s, 10s, 15s, 20s
- Gas used: Propane

Textiles and textile products -Burning behaviour - Curtains and drapes - Measurement of flame spread of vertically oriented specimens with large ignition source
(EN 13772:2011)

After 100 washes

Specimen	Lengthwise			Widthwise		
	1	2	3	1	2	3
T1 severed (Y/N)	N	N	N	N	N	N
T3 severed (Y/N)	N	N	N	N	N	N
T1 (seconds)	/	/	/	/	/	/
T3 (seconds)	/	/	/	/	/	/
Flaming debris (Y/N)	N	N	N	N	N	N

Remark:

- T1: From the start of the application of the igniting flame to the severance of the first marker thread (240mm)



- (2) T3: From the start of the application of the igniting flame to the severance of the third marker thread (540mm)
- (3) Y= Yes; N=No
- (4) Burner ignition location: Bottom edge ignition.
- (5) Ignition time: 10s.
- (6) Gas used: Propane

Classification for EN 13773:

Class	Ignitability	Flame spread
1	Non ignition according to EN 1101	1 st marker threads not severed, no flaming debris, according to EN 13772
2	Non ignition according to EN 1101	3 rd marker threads not severed, no flaming debris, according to EN 13772
3	Non ignition according to EN 1101	3 rd marker threads severed, and/or flaming debris, according to EN 13772
4	Ignition according to EN 1101	3 rd marker threads not severed, no flaming debris, according to EN 1102
5	Ignition according to EN 1101	3 rd marker threads severed, and/or flaming debris, according to EN 1102

Conclusion:

The submitted sample **complies** with the requirement of Class 1 prescribed in EN 13773:2003.

Wash procedure:ISO 6330:2021;After 100 washes, Using horizontal axis, front-loading type machine; Procedure No.4N, Machine Wash At 40°C; with 2kg total dry mass (Type III (100% Polyester) Ballast+ Specimen), 20±1 g ECE reference detergent 98 without optical brightener, Tumble Dry Normal, Not Exceeding 80°C

#This test was carried out by SGS-CSTC Standards Technical Services (SHANGHAI) Co.,Ltd.

Sample Photo



End of Report



Scan to see the report



SL42504313443701TX

Verification:
check.sgsonline.com.cn



SGS-CTC (China) Technical Services (Suzhou) Co., Ltd.
Suzhou Laboratory

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/terms-and-conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions. If any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN_Doccheck@sgs.com

Rubing Street, Rubing 18, Nanhai Science Park, Taming District, Qingzhou, Jiangsu, China 213017
中国·江苏·常州市天宁区聚牡丹科技园30幢·18幢 邮编: 213017

t (86-518) 8535 8121 www.sgggroup.com.cn
t (86-518) 8535 8121 sgs.china@sgs.com